

Données relatives à l'échantillon prélevé

Origine Genetti SA
 Emplacement Epines
 effectué par: SaPa
 Remarques: en stock Epines


Courbe analysée

GAR Riddes	16.09.05	80%
0/4 concassé Riddes	11.10.05	20%
examen de qualification selon fuseaux restreints, fr1 et fr2		

Tamis	Recette
-------	---------

mm	mélange
0.063	0.47
0.08	1.36
0.10	2.25
0.125	3.15
0.16	4.50
0.20	5.85
0.25	7.20
0.32	8.70
0.40	10.20
0.50	11.70
0.63	14.01
0.80	16.32
1.00	18.64
1.25	22.13
1.60	25.62
2.00	29.11
2.50	33.27
3.15	37.43
4.00	41.59
5.00	45.92
6.30	50.25
8.00	54.58
10.00	63.12
12.50	71.65
16.00	80.18
20.00	85.86
25.00	91.54
31.50	97.22
45.00	98.61
63.00	100.00
90.00	100.00

Courbe de composition de la grave selon SN 670 120c



courbe et explicatifs diponibles sur www.genetti.ch